

**PP/PE RECYCLED PELLETS**

<b>Commercial Name</b>	MIXLENE		
<b>Application</b>	INJECTION MOULDING	<b>Test Date</b>	15/02/2017

VALUE	TEST METHOD	RESULT
MFI	ISO 1133 g/10 min. 2,16Kg.230°	12 (+2/-2)
DENSITY	ISO 1183 g/cc	0.92 (+/- 0,2)
TRACTION RESISTANCE	ISO 527 Mpa (5mm/min)	23
IMPACT RESISTANCE	23° kJ/m2	8
CARBON BLACK	ISO 6964	-----
ASHES	ISO 3451	Max 2%



- . NOT FOR FOOD CONTACT
- . HOMOGENEOUS LOT 25 TN
- . PACKAGING 1.250 KGS BIG BAG
- . 150 MICRONS LASER FILTERED